



中国认可
国际互认
检测
TESTING
CNAS L10314



No: 200043547

APPLICANT: GUANGZHOU CHUANGWEI LABOR PROTECT
ADDRESS: NO. 401, 50TH GUIYAN STREET, DALON

APPLICANT PROVIDED SAMPLE DESCRIPTION:

VE
VE

TEST REPORT

检验检测报告



广州检验检测认证集团有限公司
Guangzhou Inspection Testing and Certification Group Co., Ltd.
广州广检纺织服装服饰检测研究院有限公司
Guangzhou Guangjian Textile Garment and Accessories Testing and Research Institute Co., Ltd.
国家纺织品服装服饰产品质量检验中心(广州)
National Quality Inspection and Testing Center for Textile Garment and Accessories(Guangzhou)
国家皮革制品质量检验中心(广东)
National Quality Inspection and Testing Center for Leather Products (Guangdong)



TEST REPORT



No: 200043547

VERIFICATION WEBSITE: www.gttc.net.cn

VERIFICATION CODE: RLGW-3523-44



ISSUE DATE: 2020-03-20

APPLICANT: GUANGZHOU CHUANGWEI LABOR PROTECTION APPLIANCE CO., LTD.
ADDRESS: NO. 401, 50TH GUIYAN STREET, DALONG STREET, PANYU DIST. GZ.

APPLICANT PROVIDED SAMPLE DESCRIPTION:
FIFTY(50) PIECES OF PROFESSIONAL PROTECTIVE MASK
BRAND: LianYoU

DATE RECEIVED/DATE TEST STARTED: 2020-03-19

CONCLUSION:

FILTRATION EFFICIENCY TO NaCl PARTICULATE MATTER	M
INSPIRATORY RESISTANCE	M
EXPIRATORY RESISTANCE	M
HEAD BAND	M

NOTE: "M" -MEET THE STANDARD'S REQUIREMENT "F" -FAIL TO MEET THE STANDARD'S REQUIREMENT
"___" -NO COMMENT

REMARK:

THIS REPORT IS THE ENGLISH TRANSLATION VERSION OF THE REPORT 200008557.
ALL THE TESTED ITEMS ARE TESTED UNDER THE STANDARD CONDITION (EXCEPT FOR INDICATION).
COPIES OF THE REPORT ARE VALID ONLY RE-STAMPED.
THE EXPERIMENT WAS CARRIED OUT AT No. 1, ZHUJIANG ROAD, PANYU DISTRICT, GUANGZHOU, GUANGDONG, P. R. CHINA.

5.1.2e

5.1.2e

APPROVED BY:

Nan Ma ENGINEER

PAGE 1 OF 3

TEST REPORT

No:200043547



5.1.2e



TEST REPORT

No:200043547

FILTRATION EFFICIENCY TO NaCl PARTICULATE MATTER

(GB 2626-2006 6.3, AIR FLOW:85L/min, AEROSOL:NaCl, AEROSOL CONCENTRATION:15mg/m³,
TEMP:23.0°C, RH:35.6%)

FILTRATION EFFICIENCY (%):

UNTREATED SAMPLE

1# 99.732
2# 99.825
3# 99.741
4# 99.753
5# 99.809
6# 99.752
7# 99.747
8# 99.810
9# 99.847
10# 99.801

CONDITIONING TREATED

1# 99.500
2# 99.469
3# 99.581
4# 99.576
5# 99.480

REQUIREMENT

FILTRATION EFFICIENCY (%):

≥95.0
(KN95)
(GB 2626-2006)

INSPIRATORY RESISTANCE (Pa)

(GB 2626-2006 6.5)

UNTREATED SAMPLE:

1# 132.1
2# 128.5

PRETREATMENT SAMPLE:

1# 124.9
2# 126.7

REQUIREMENT

≤350
(GB 2626-2006)

EXPIRATORY RESISTANCE (Pa)

(GB 2626-2006 6.6)

UNTREATED SAMPLE:

1# 98.5
2# 102.8

PRETREATMENT SAMPLE:

1# 95.3
2# 96.8

REQUIREMENT

≤250
(GB 2626-2006)

HEAD BAND

(GB 2626-2006 6.11)

UNTREATED SAMPLE:

1# PASS

CONDITIONING TREATED:

1# PASS

REQUIREMENT

ACCORDING TO THE CLAU
PRODUCT STANDARD
(GB 2626-2006)

5.1.2e

—End of Report—

PAGE 3 OF 3

注意事项

1. 报告书未加盖检测单位检验检测专用章无效。
2. 复印件未加盖检测单位报告确认章无效。
3. 对委托送检结果有异议的,应于报告书送达之日起十五日内提出。
4. 检测结果仅对所检样品有效。
5. 未取得资质认定的项目,仅作为科研、教学或内部质量控制之用。
6. 报告书涂改无效。

NOTE

1. The report is invalid without authorized stamp.
2. Copies of this report are invalid without authorized stamp.
3. Any dispute should be raised within 15 days after receiving the report.
4. The result is only valid for the tested sample.
5. The results of unapproved items are for reference only.
6. This report is invalid if altered.

总部:

广州市番禺区珠江路1号

电话:020-5.1.2e

网址: <http://www.gttc.net.cn>

Headquarters:

Add: No.1, Zhujiang Road, Panyu District, Guangzhou,
Guangdong, P.R.China.

Tel: +86-5.1.2e

Web: <http://www.gttc.net.cn>

花都实验室:

广州市花都区狮岭镇旗岭河滨西路1号

电话:020-5.1.2e

Huadu Laboratory:

Add: No.1 Hebin West Road, Qiling, Huadu District, Guangzhou,
Guangdong, P.R.China.

Tel: +86-5.1.2e

中大工作站:

广州市海珠区瑞康路389号长江轻纺城(新长江)南区3层
SC044号

电话:020-5.1.2e

Zhongda Office:

Add: Room SC044, 3/F Southern Area, Changjiang (China) Fabrics & Accessories
Center, No.389 Ruikang Road, Haizhu District, Guangzhou,
Guangdong, P.R.China.

Tel: +86-5.1.2e

白马工作站:

广州市越秀区站南路16号白马大厦负一层招商中心旁

电话:020-5.1.2e

Baima Office:

Add: -1/F, Baima Building, No.16 Zhannan Road, Yuexiu District, Guangzhou,
Guangdong, P.R.China.

Tel: +86-5.1.2e

西安分公司:

西安市碑林区南关正街88号长安国际F座1201室

电话:029-5.1.2e

Xian Branch:

Add: F1201 Chang'an Metropolis Center, 88 Nanguan Street, Beilin District,
Xian, P.R.China.

Tel: +86-5.1.2e